

Article

Synthesis of Substituted 1,4-Diazepines and 1,5-Benzodiazepines Using an Efficient Heteropolyacid-Catalyzed Procedure

Rachedine Kaoua¹, Norah Bennamane¹, Saliha Bakhta^{1,2}, Sihame Benadji^{2,3}, Cherifa Rabia³ and Bellara Nedjar-Kolli^{1,*}

¹ Laboratory of Applied Organic Chemistry, Houari Boumediene University of Sciences and Technology, BP 31, El-Alia, Bab-Ezzouar, 16111, Algiers, Algeria

² Center of Research in Physical and Chemical Analysis CRAPC, BP 248, Algiers RP 16004, Algiers, Algeria

³ Laboratory of Natural Gas, Houari Boumediene University of Sciences and Technology, BP 31, El-Alia, Bab-Ezzouar 16111, Algiers, Algeria

* Author to whom correspondence should be addressed; E-Mail: bnkollidz@gmail.com.

Received: 19 November 2010 / Accepted: 11 December 2010 / Published: 28 December 2010

Abstract: An efficient and improved procedure for the synthesis of 1,4-diazepine and 1,5-benzodiazepine derivatives via the reaction of ketimine intermediates with aldehydes in the presence of Keggin-type heteropolyacids (HPAs) was developed. High yields and short reaction times were obtained for both electron-releasing and electron-withdrawing substituted 1,4-diazepine and 1,5-benzodiazepines derivatives.

Keywords: 1,4-diazepine; 1,5-benzodiazepine; dehydroacetic acid; 1,3-aminomethyl propane; orthophenylene diamine; heteropolyacids

1. Introduction

Diazepines and benzodiazepines have various therapeutic applications. Many members of the diazepine family are widely used as anticonvulsants, antianxiolitics, analgesics, sedatives, antidepressives and hypnotic agents [1-4]. Benzodiazepine derivatives are used as dyes for acrylic fibers [5]. In addition, benzodiazepines are valuable intermediates for the synthesis of fused ring compounds such as triazolo-, oxadiazolo-, oxazino-, and furanobenzodiazepines [6-11].


Due to their wide range of pharmacological activity and industrial applications, the development of mild and efficient protocols for their preparation continues to be a challenging endeavor in the synthetic organic chemistry [12-28]. The common procedure for the synthesis of these compounds is a one pot condensation between *o*-phenylenediamines and carbonyl compounds [29]. However, a large number of the modified methods reported in the literature, suffer from several drawbacks such as the use of a large amount of catalysts, unsatisfactory product yields and critical product isolation procedures. These disadvantages require a development of an efficient and practically useful process of preparation [30].

In recent years, the use of polyoxometalates as catalysts in homogeneous and heterogeneous systems has attracted great interest in organic synthesis because their acidic and redox properties can be controlled at the molecular or atomic level and they also offer economical and environmental benefits [31-35].

Among the different classes of polyoxometalates, the Keggin-type heteropolyacids (HPAs) offer a strong option for efficient and cleaner processing compared to polluting and corrosive liquid acid catalysts [36]. They have the particularity of possessing multi-functional properties as strong Brønsted acidity and strong redox power. Their use allows reductions of costs and waste generation through reuse and recycling [37,38].

We report here for the first time the synthesis of 1,4-diazepines **4** from enaminones **2** in the presence of both CF₃COOH and Keggin type HPA catalysts. 1,5-Benzodiazepines **5** have also been prepared, again in the presence of the HPA catalysts [29].

Scheme 1. Synthesis of 1,4-benzodiazepines **4** and 1,5- benzodiazepines **5**.



2. Results and Discussion

Previously, we have synthesized 1,5-benzodiazepine **5** products [29] from the reaction between product **3** and aromatic aldehydes in the presence of catalytic amounts of trifluoroacetic acid in ethanol under reflux conditions. In continuation of this work on the synthesis of diazepine rings, we have now prepared a series of novel 1,4-diazepines **4** from derivatives **2** following to the same procedure (Scheme 1). The results (Table 1) show that the reaction is slow with unsatisfactory yields.

Table 1. Synthesis of 1,4-diazepine and 1,5-benzodiazepine derivatives using CF_3COOH as catalyst under reflux conditions.

Compounds	R	Ratio of aldehyde	CF_3COOH
			Times (min) / Yields (%)
4a	C_6H_5	1.5	420/60
4b	<i>p</i> - $\text{CH}_3\text{C}_6\text{H}_5$	1.5	420/55
4c	<i>p</i> - ClC_6H_5	2.5	360/64
4d	<i>p</i> - BrC_6H_5	2.5	360/69
5a	C_6H_5	1.5	360/79
5b	<i>p</i> - $\text{CH}_3\text{C}_6\text{H}_5$	1.5	420/83
5c	<i>p</i> - ClC_6H_5	3	720/64
5d	<i>p</i> - BrC_6H_5	3	720/74

Due to strong Brønsted acidity and high oxidative power of Keggin type HPAs, that give them a bifunctional character, we decided to test the following series of HPAs in the preparation of derivatives **4** and **5**: $\text{H}_3\text{PW}_{12}\text{O}_{40}$ and $\text{H}_{3+x}\text{PMo}_{12-x}\text{V}_x\text{O}_{40}$, with $x = 0-3$, as catalysts. The obtained results are shown in Table 2.


Table 2. Synthesis of 1,4-diazepine and 1,5-benzodiazepine derivatives using equimolar reactants in presence of various heteropolyacids under refluxing conditions.

Compounds	R	$\text{H}_3\text{PW}_{12}\text{O}_{40}$	$\text{H}_3\text{PMo}_{12}\text{O}_{40}$	$\text{H}_4\text{PMo}_{11}\text{VO}_{40}$	$\text{H}_5\text{PMo}_{10}\text{V}_2\text{O}_{40}$	$\text{H}_6\text{PMo}_9\text{V}_3\text{O}_{40}$
		Times (min) / Yields (%)				
4a	C_6H_5	600/72	300/69	180/70	30/85	60/83
4b	<i>p</i> - $\text{CH}_3\text{C}_6\text{H}_5$	660/75	300/79	180/77	30/80	60/83
4c	<i>p</i> - ClC_6H_5	640/69	300/73	180/73	30/78	60/74
4d	<i>p</i> - BrC_6H_5	600/75	300/71	180/72	30/75	60/77
5a	C_6H_5	420/87	220/79	120/85	15/90	40/78
5b	<i>p</i> - $\text{CH}_3\text{C}_6\text{H}_5$	390/82	220/83	120/82	15/88	40/89
5c	<i>p</i> - ClC_6H_5	360/70	220/77	120/75	15/93	40/87
5d	<i>p</i> - BrC_6H_5	360/76	220/73	120/74	15/91	40/94

The catalysts were used with equimolar amounts of reactants in refluxing ethanol; the reaction proceeded smoothly, affording the products in good to excellent yields. The results indicate that the catalytic activity depends on the composition of the catalyst. The substitution of one to three molybdenum atoms by vanadium atoms decreases the reaction time and increases the product yields. This can be attributed to the character more oxidative and less acidic compared to those of $H_4PMo_{11}VO_{40}$, $H_3PMo_{12}O_{40}$ and $H_3PW_{12}O_{40}$ [31,35,38]. As shown in Table 2, the order of efficiency follows the sequence: $H_5PMo_{10}V_2O_{40} > H_6PMo_9V_3O_{40} > H_4PMo_{11}VO_{40} > H_3PMo_{12}O_{40} > H_3PW_{12}O_{40}$. Since the best results in term of yield and reaction time have been achieved with $H_5PMo_{10}V_2O_{40}$, this was selected for its better catalytic performance for the synthesis of diazepine rings.

To optimize the reaction, temperature and molar ratio of $H_5PMo_{10}V_2O_{40}$ catalyst and reactants were checked. No reaction was detected at room temperature. Intramolecular cyclization of **2** or **3** via respectively intermediate **A** or **B** (Scheme 2) under reflux conditions in the presence of only 0.1 % of $H_5PMo_{10}V_2O_{40}$ catalyst is enough to drive the reaction forward; higher amounts of catalysts did not improve the results.

Scheme 2. Synthetic route to compounds **4** and **5**.



It is difficult to clarify how HPAs acts as a catalyst in this reaction. On the basis of a previously reported mechanism [29], it was suggested that the formation time of derivatives **5** depends on the nature of the substituent R on the aldehyde ring. Formation of **5** is particularly rapid when R is a strong donor group, whereas a withdrawing substituent inhibits the formation of compounds **5**. Yields are also affected by electronic effects and they significantly increased by using an excess of aldehyde (Table 1). Similarly, intermediate **A** undergoes intramolecular cyclization under acidic conditions, according to the described conditions [29] leading to products **4**. Yields and reaction times are very comparable to those obtained with intermediate **B**. These results can be explained by the nature of substituent R as shown in Table 1. When the optimized conditions (in presence of HPAs) are applied to substrates, high yields of **4** and **5** are obtained. These results show that the electronic nature of the substituent seems not to have a great effect on the reaction yields and that both acidic and redox properties of the heteropolyacids are involved during the synthesis.

The nature and the composition of the polyanion have an important effect on the catalytic properties of the HPAs. However, it is very difficult to clarify the difference between catalytic behaviour of these systems in this reaction. We believe that there is a complex relationship between the activity, the chemical composition and the position of the vanadium atoms in the Keggin polyanions.

3. Experimental

3.1. General

Melting points were measured on a Buchi 512 apparatus and were uncorrected. FTIR spectra were taken in Nujol on a Perkin–Elmer spectrometer. The $^1\text{H-NMR}$ spectra (250 and 300 MHz) and $^{13}\text{C-NMR}$ (63 MHz) were run on a Bruker spectrometer in CDCl_3 using tetramethylsilane as internal standard. The impact ionisation (IE) mass spectra were recorded on a Nermag R-10-10C at 70 eV. Chemicals were purchased from Aldrich and Fluka. Compounds **2** and **3** were prepared according to the literature [39]. All the products were identified by comparison of analytical data (mp, NMR) with those reported (in the case of derivatives **5**) or with authentic samples prepared by the conventional method using CF_3COOH as catalyst (in the case of compounds **4**).

3.2. Catalyst preparation

Phosphomolybdic and phosphotungstic acid samples, $\text{H}_3\text{PMo}_{12}\text{O}_{40}$ and $\text{H}_3\text{PW}_{12}\text{O}_{40}$ were obtained according to the method of Tsigdinos [40] by heating MoO_3 (WO_3) with a solution of diluted H_3PO_4 . Synthesis of mono-, di- and tri-vanadium substituted phosphomolybdic acids, $\text{H}_{3+x}[\text{PMo}_{12-x}\text{V}_x\text{O}_{40}]$ ($x = 1-3$) was carried out according to the procedure of Tsigdinos and Hallada [41] by acidifying with concentrated H_2SO_4 an appropriate mixture solutions of Na_2HPO_4 , Na_2MoO_4 and NaVO_3 in appropriate molar ratio. The HPAs formed were extracted with diethyl ether.

3.3. General procedure for the heteropolyacid-Keggin acid catalyzed synthesis of derivatives **4** and **5**

A mixture of **2** or **3** (10 mmol) and aldehyde (10 mmol) in presence of Keggin acid catalyst (1% mmol) dissolved in ethanol (15 mL) was refluxed with stirring for the indicated time (see Table 2). The reaction was followed by TLC. When the reaction time was over, the organic solution was concentrated in vacuum. Then the compounds were filtered and washed twice with ethanol (2×10 mL). The catalyst was recovered after evaporating of ethanol.

3-(2,2-Dimethyl-7-phenyl-2,3,6,7-tetrahydro-1H-1,4-diazepin-5-yl)-4-hydroxy-6-methyl-2H-pyran-2-one (4a). Yellow solid, m.p. 186 °C; $^1\text{H-NMR}$ (CDCl_3 , 250 MHz): δ 1.45 (s, 3H, CH_3), 1.48 (s, 3H, CH_3), 2.13 (s, 3H, CH_3), 3.58 (s, 2H, $\text{CH}_2\text{-N=}$), 4.32 (t, 1H, $J = 9$ Hz, CH-Ar), 4.75 (dd, 2H, $J = 9, 2$ Hz, $\text{CH}_2\text{-CH}$), 5.85 (s, 1H, $=\text{CH}$), 7.16-7.37 (m, 5H, H-Ar), 7.52 (s, 1H, NH), 13.80 (s, 1H, OH); $^{13}\text{C-NMR}$ (CDCl_3): δ 20, 22, 30, 52, 53, 55, 62, 96, 108, 128, 129, 132, 143, 163, 164, 179, 184; MS m/z (%): 326 ($[\text{M}]^+$, 6), 235 (19), 181 (60), 151 (27), 136 (14), 43 (37).

3-[2,2-Dimethyl-7-(4-methylphenyl)-3,6-dihydro-2H-1,4-diazepin-5-yl]-4-hydroxy-6-methyl-2H-pyran-2-one (4b). Yellow solid, m.p. 220 °C; $^1\text{H-NMR}$ (CDCl_3 , 250 MHz): δ 1.37 (s, 3H, CH_3), 1.38 (s, 3H, CH_3), 2.14 (s, 3H, CH_3), 2.24 (s, 3H, CH_3), 3.54 (s, 2H, $\text{CH}_2\text{-N=}$), 4.17 (t, 1H, $J = 9$ Hz, CH-Ar), 4.70 (dd, 2H, $J = 9, 2$ Hz, $\text{CH}_2\text{-CH}$), 5.75 (s, 1H, $=\text{CH}$), 7.00-7.10 (d, 2H, $J = 8.3$ Hz, H-Ar), 7.10-7.20 (d, 2H, $J = 8.1$ Hz, H-Ar), 7.80 (s, 1H, NH), 14.03 (s, 1H, OH); $^{13}\text{C-NMR}$ (CDCl_3): δ 20, 21, 32, 51, 53, 55, 61, 95, 108, 128 - 129, 134, 146, 163, 164, 178, 18; MS m/z (%): 340 ($[\text{M}]^+$, 2), 235 (16), 181 (40), 151 (4), 136 (1), 43 (70).

3-[7-(4-Chlorophenyl)-2,2-dimethyl-2,3,6,7-tetrahydro-1H-1,4-diazepin-5-yl]-4-hydroxy-6-methyl-2H-pyran-2-one (**4c**). Yellow solid, m.p. 223 °C; ¹H-NMR (CDCl₃, 250 MHz): δ 1.38 (s, 3H, CH₃), 1.39 (s, 3H, CH₃), 2.15 (s, 3H, CH₃), 3.65 (s, 2H, CH₂-N=), 4.39 (t, 1H, *J* = 9 Hz, CH-Ar), 4.70 (dd, 2H, CH₂, *J* = 9, 2 Hz, CH₂-CH), 5.90 (s, 1H, =CH), 7.20-7.25 (m, 2H, H-Ar), 7.25-7.30 (m, 2H, H-Ar), 7.96 (s, 1H, NH), 13.82 (s, 1H, OH); ¹³C-NMR (CDCl₃): δ 19, 20, 30, 50, 54, 55, 63, 96, 105, 129, 130, 133, 136, 165, 166, 177, 182; MS *m/z* (%): 360 ([M]⁺, 24), 235 (14), 181 (100), 151 (8), 136 (8), 43 (28).

3-[7-(4-bromophenyl)-2,2-dimethyl-2,3,6,7-tetrahydro-1H-1,4-diazepin-5-yl]-4-hydroxy-6-methyl-2H-pyran-2-one (**4d**). Yellow solid, m.p. 245 °C; ¹H-NMR (CDCl₃, 250 MHz): δ 1.44 (s, 3H, CH₃), 1.47 (s, 3H, CH₃), 2.15 (s, 3H, CH₃), 3.62 (s, 2H, CH₂-N=), 4.36 (t, 1H, *J* = 9 Hz, CH-Ar), 4.70 (dd, 2H, *J* = 9, 2 Hz, CH₂-CH), 5.90 (s, 1H, =CH), 7.10-7.20 (m, 2H, H-Ar), 7.35-7.45 (m, 2H, H-Ar), 7.99 (s, 1H, NH), 13.79 (s, 1H, OH); ¹³C-NMR (CDCl₃): δ 19, 20, 34, 53, 54, 56, 60, 95, 107, 130, 131, 135, 145, 163, 165, 178, 181; MS *m/z* (%): 371 ([M]⁺, 0.5), 235 (18), 181 (20), 151 (3), 136 (5), 43 (66).

4. Conclusions

We present here the synthesis of a new series of 1,4-benzodiazepine derivatives **4** using two different catalyst classes, a conventional catalyst, CF₃COOH, and HPAs. The results have shown the superior catalytic efficiency of the heteropolyacids. The principal features of the methodology using HPAs as catalyst are high-yields and shorter reaction times for both electron-releasing and electron-withdrawing substituted derivatives **4** and **5**, substances with potentially interesting biological and medicinal properties.

References and Notes

1. Schutz, H. *Benzodiazepines*; Springer: Heidelberg, Germany, 1982.
2. Landquist, J.K. *Comprehensive Heterocyclic Chemistry*; Katritzky, A.R., Rees, C.W., Eds.; Pergamon: Oxford, UK, 1984; Volume 1, pp. 166-170.
3. Fryer, R.I. Bicyclic Diazepines. In *Comprehensive Heterocyclic Chemistry*; Taylor, E.C., Ed.; Wiley: New York, NY, USA, 1991; Volume 50, Chapter II.
4. Randall, L.O.; Kappel, B. *Benzodiazepines*; Garattini, S., Musini, E., Randall, L.O., Eds.; Raven Press: New York, NY, USA, 1973; p. 27.
5. Harris, R.C.; Straley, J.M. Cationic polymethine dyes for acrylic fibers. *U.S. Patent 1,537,757*, 1968; [*Chem. Abstr.* **1970**, 73, 100054w].
6. Bennamane, N.; Kaoua, R.; Hammal, L.; Nedjar-Kolli, B. Synthesis of new amino-1,5-benzodiazepine and benzotriazole derivatives from dimedone. *Org. Commun.* **2008**, 1, 62-68.
7. Hammal, L.; Bouzroua, S.; André, C.; Nedjar-Kolli, B.; Hoffmann, P. Versatile Cyclization of Aminoanilino Lactones: Access to Benzotriazoles and Condensed Benzodiazepin-2-thiones. *Synt. Commun.* **2007**, 37, 501-511.
8. Aversa, M.C.; Ferlazzo, A.; Gionnetto, P.; Kohnke, F.H. A convenient synthesis of novel [1,2,4]triazolo[4,3-*a*][1,5]benzodiazepine derivatives. *Synthesis* **1986**, 3, 230-231.

9. Essaber, M.; Hasnaoui, A.; Benharref, A.; Lavergne, J.P. Synthesis of new tri- and tetraheterocyclic systems: 1,3-dipolar cycloaddition of nitrilimines on 2,7-dimethyl-4-phenyl-3H-1,5-benzodiazepin. *Synth. Commun.* **1998**, *28*, 4097-4104.
10. El-Sayed, A.M.; Abdel-Ghany, H.; El-Saghier, A.M.M. A novel synthesis of pyrano(2,3-c)-, 1,3-oxazino(2,3 b)-, 1,2,4-triazolo(3,4-b)-, oxazolo(2,3-b)-, furano(3,2-c)-, and 3-substituted-(1,5)benzodiazepin-2-ones. *Synth Commun.* **1999**, *29*, 3561-3572.
11. Chimirri, A.; Grasso, S.; Ottana, R.; Romeo, G.; Zappala, M. Synthesis and stereochemistry of novel [1,2,4]oxadiazolo[4,5-a][1,5]benzodiazepine derivatives. *J. Heterocycl. Chem.* **1990**, *27*, 371-374.
12. Herbert, J.A.L.; Suschitzky, H. Syntheses of heterocyclic compounds. Part XXIX. Substituted 2,3-dihydro-1H-1,5-benzodiazepines. *J. Chem. Soc., Perkin Trans.* **1974**, *1*, 2657-2661.
13. Morales, H.R.; Ulbarela, B.A.; Contreras, R. New synthesis of dihydro- and tetrahydro-1,5-benzodiazepines by reductive condensation of *o*-phenylenediamine and ketones in the presence of sodium borohydride. *Heterocycles* **1986**, *24*, 135-139.
14. Jung, D.I.; Choi, T.W.; Kim, Y.Y.; Kim, I.S.; Park, Y.M.; Lee, Y.G.; Jung, D.H. Synthesis of 1,5-benzodiazepine derivatives. *Synth. Commun.* **1999**, *29*, 1941-1951.
15. Balakrishna, M.S.; Kaboudin, B. A simple and new method for the synthesis of 1,5 benzodiazepine derivatives on a solid surface. *Tetrahedron Lett.* **2001**, *42*, 1127-1129.
16. Curini, M.; Epifano, F.; Marcotullio, M.C.; Rosati, O. Corrigendum to Ytterbium triflate promoted synthesis of 1,5-benzodiazepine derivatives. *Tetrahedron Lett.* **2001**, *42*, 3193-3195.
17. Kaboudin, B.; Navaee, K. Alumina/Phosphorus Pentoxide (App) as an Efficient Reagent for the Synthesis of 1,5-Benzodiazepines under Microwave Irradiation. *Heterocycles* **2001**, *55*, 1443-1446.
18. Pozarentzi, M.; Stephanatou, J.S.; Tsoleridis, C.A. An Efficient Method for the Synthesis of 1,5-Benzodiazepine Derivatives under Microwave Irradiation without Solvent. *Tetrahedron Lett.* **2002**, *43*, 1755-1758.
19. Yadav, J.S.; Reddy, B.V.S.; Eshwaraiah, B.; Anuradha, K. Amberlyst-15: Anovel and recyclable reagent for the synthesis of 1,5-benzodiazepines anionic liquids. *Green Chem.* **2002**, *4*, 592-594.
20. Sabitha, G.; Reddy, G.S.K.K.; Reddy, K.B.; Reddy, N.M.; Yadav, J.S. A new, efficient and environmentally benign protocol for the synthesis of 1,5-benzodiazepines using cerium (III) chloride/sodium iodide supported on silica gel. *Adv. Synth. Catal.* **2004**, *346*, 921-923.
21. Yadav, J.S.; Reddy, B.V.S.; Kumar, S.P.; Nagaiah, K. Indium(III) bromide: A novel and efficient reagent for the rapid synthesis of 1,5-benzodiazepines under solvent-free conditions. *Synthesis* **2005**, 480-484.
22. Jarikote, D.V.; Siddiqui, S.A.; Rajagopal, R.; Daniel, T.; Lahoti, R.J.; Srinivasan, K.V. Room temperature ionic liquid promoted synthesis of 1,5- benzodiazepine derivatives under ambient conditions. *Tetrahedron Lett.* **2003**, *44*, 1835-1838.
23. De, S.K.; Gibbs, R.A. Scandium(III) triflate as an efficient and reusable catalyst for synthesis of 1,5-benzodiazepine derivatives. *Tetrahedron Lett.* **2005**, *46*, 1811-1813.
24. Varala, R.; Ramu, E.; Sreelatha, N.; Adapa, S.R. Ceric ammonium nitrate (CAN) promoted efficient synthesis of 1,5-benzodiazepine derivatives. *Synlett* **2006**, 1009-1014.

25. Pasha, M.A.; Jayashankara, V.P. Synthesis of 1,5-benzodiazepine derivatives catalyzed by zinc chloride. *Heterocycles* **2006**, *68*, 1017-1023.
26. Kumar, R.; Chaudhary, P.; Nimesh, S.; Verma, A.K.; Chandra, R. An efficient synthesis of 1,5-benzodiazepine derivatives catalyzed by silver nitrate. *Green Chem.* **2006**, *8*, 519-521.
27. Reddy, B.M.; Sreekanth, P.M.; Lakshmanan, P. Sulfated zirconia as an efficient catalyst for organic synthesis and transformation. *J. Mol. Catal. A: Chem.* **2005**, *237*, 93-100.
28. Yadav, J.S.; Reddy, B.V.S.; Satheesh, G.; Srinivasulu, G.; Kunwar, A.C. InCl₃-catalyzed stereoselective synthesis of optically pure 1,5-benzodiazepines. *Arkivoc* **2005**, *iii*, 221-227.
29. Fodili, M.; Amari, M.; Kolli, B.; Robert, A.; Baudy-Floch, M.; Le Grel, P. An efficient Synthesis of New 2-pyronyl-1,5-benzodiazepine derivatives. *Synthesis* **1999**, *5*, 811-814.
30. Heravi, M.M.; Sadjadi, S.; Oskooie, H.A. An Efficient Synthesis of 3H-1,5-benzodiazepine Derivatives Catalyzed by Heteropolyacids as a Heterogeneous Recyclable Catalyst. *J. Chin. Chem. Soc.* **2008**, *55*, 842-845.
31. Khozhevnikov, I.V. Catalysis by heteropolyacids and multicomponent polyoxometalates in liquid-phase reactions. *Chem. Rev.* **1998**, *98*, 171-198.
32. Ono, Y.; Thomas, J.M.; Zamaraev, K.I., Eds. *Perspectives in Catalysis*; Blackwell: London, UK, 1992; p. 341.
33. Khozhevnikov, I.V.; Matveev, K.I. Homogeneous Catalysts Based on Heteropolyacids. *Appl. Catal.* **1983**, *5*, 135-150.
34. Izumi, Y.; Urabe, K.; Onaka, A. *Zeolite, Clay and Heteropolyacids in Organic Chemistry*; Kodansha, Tokyo-VCH: Weinheim, Germany, 1992; p. 99.
35. Khozhevnikov, I.V. Heteropolyacids and related compounds as catalysts for fine chemical synthesis. *Catal. Rev.-Sci. Eng.* **1995**, *37*, 311-352.
36. Heravi, M.M.; Derikvand, F.; Haeri, A.; Oskoeie, H.A.; Bamoharram, F.F. Heteropolyacids as Green and Reusable Catalysts for the Synthesis of Isoxazole Derivatives. *Synth. Commun.* **2008**, *38*, 135-140.
37. Schwegler, M.A.; Bekkum, H.; Van Munck, N. Heteropolyacids as catalysts for the production of phthalate diesters. *Appl. Catal.* **1991**, *74*, 191-204.
38. Mizuno, N.; Misono, M. Studies of the activity of catalysts based on heteropolyacids. *J. Mol. Catal.* **1994**, *86*, 319-342.
39. Maiti, B.C.; Maitra, S.K. Reaction of dehydroacetic acid with aliphatic, aromatic and heterocyclic amines. *Indian J. Chem.* **1998**, *37*, 710-712.
40. Tsigdinos, G.A. Preparation and Characterization of 12-Molybdophosphoric and 12-Molybdosilicic Acids and Their Metal Salts. *Ind. Eng. Chem., Prod. Res. Dev.* **1974**, *13*, 267-274.
41. Tsigdinos, G.A.; Hallada, C.J. Molybdovanadophosphoricacids and their salts (I) Investigation of methods of preparation and characterization. *Inorg. Chem.* **1968**, *7*, 437-441.

Sample Availability: Samples of the compounds are available from the authors.