

Single-crystal structure of $K_3 Nb_8 O_{21}$

Authors

Abderrahim Benabbas

Publication date

1993

Publisher

university bouira

Description

Description Tripotassium 21-oxooctaniobate, $M_r = 1196.53$, hexagonal, $P6_3/mcm$, $a = 9.1584$ (5), $c = 12.0404$ (4) Å, $V = 874.6$ (1) Å³, $Z = 2$, $D_x = 4.54$ Mg m⁻³, $\lambda(\text{Mo K } \alpha) = 0.71073$ Å, $\mu = 5.65$ mm⁻¹, $F(000) = 1106$, $T = 294$ K, $R = 0.044$, $wR = 0.047$ for 2540 reflections with $I > 3\sigma(I)$. The framework is built up from $[Nb_6 O_{24}]$ units stacked along c giving $[Nb_6 O_{21}]_\infty$ chains which are held together by single NbO_6 octahedra.(orig.).