

Redetermination of the structure of $\text{PNb}_9\text{O}_{25}$

Authors

A Benabbas, MM Borel, A Grandin, A Leclaire, B Raveau

Publication date

1991/4/15

Description

Nonaniobium phosphorus pentacosaoxide, $\text{PNb}_9\text{O}_{25}$, $M_r = 1267.11$, tetragonal, $I4/m$, $a = 15.639(2)$, $c = 3.8317(4)$ Å, $V = 937.1(3)$ Å³, $Z = 2$, $D_x = 4.49$ Mg m⁻², $\lambda(\text{MoK}\alpha) = 0.71073$ Å, $\mu(\text{MoK}\alpha) = 5.27$ mm⁻¹, $F(000) = 584$, $T = 294$ K, 316 reflections with $I > 3\sigma(I)$, $R = 0.033$, $wR = 0.031$. The framework is composed of ReO_3 -type $3 \times 3 \times \infty$ columns. Each column shares edges with the four neighboring columns and corners with the PO_4 tetrahedra.(orig).